

TECHNICAL DATA SHEET

EPDM+ MEMBRANE ADHESIVE



EPDM+ Membrane Adhesive

A high-performance adhesive and sealant product that ensures seamless bonding of EPDM membranes to various non-porous construction materials.

TECHNICAL DATA

■ Basis	Neutral
■ Consistency	Thixotropic
■ Curing system	Moisture curing
■ Tack-free time	Ca. 20 mins
■ Skin Formation* (20°C/65% R.H)	4,5-5 mm / 24 h
■ Hardness (DIN 53505)	30 ± 5 Shore A
■ Density	1,35± 0,02
■ Temperature resistance (Cured)	-40°C +180°C
■ Elastic recovery (ISO 7389)	> %75
■ Max tension %100 (DIN 53504)	1,20 N/mm ²
■ Elongation at break (DIN 53504)	> 350
■ Application temperature	5°C -40°C

APPLICATIONS AREAS

- Used for bonding EPDM membranes employed in exterior facade sealing applications.
- Ensures adhesion of EPDM membranes to non-porous construction materials.

SPECIFICATIONS

- Flexible and bonds extremely strongly.
- Does not shrink over time.
- Delivers high performance in EPDM membrane applications.
- Offers excellent UV resistance.
- Does not sag on vertical surfaces.

TECHNICAL DATA SHEET

EPDM+ MEMBRANE ADHESIVE

NOTES

- Not recommended for use on porous surfaces such as granite and marble.
- Not suitable for aquariums.

SURFACE PREPERATION

- Surfaces that will come into contact with EPDM+ Membrane Adhesive must be clean and dry, free of oil, rust, and loose particles.
- If EPDM+ Membrane Adhesive has been previously applied on the surface, it must be removed using mechanical methods.
- Non-porous surfaces should be cleaned with an appropriate solvent, ensuring that the solvent is wiped off before it evaporates.
- Applying masking tape around the application joints not only prevents the adhesive from spreading onto the surrounding areas but also ensures a more aligned application. The masking tape should be removed immediately after the application.

PACKAGING (Volume)

600ml x 12 koli

SHELF LIFE

15 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C.

COLORS



Black



MANUFACTURER:
PROMAST Kimya San. Tic. A.Ş. Ovacık Mh.
Hacıoğlu Sk. No:21 B/0 41140 Başiskele
KOCAELİ | TURKEY T: +90 (262) 335 41 82
F: +90 (262) 335 41 83

